

CLAIMS

Please amend the claims to read as follows wherein changes in a claim are shown by strikethrough or double brackets for deleted matter and underlining for added matter:

1. (Currently Amended) Metal screen material having a flat side without projecting parts, comprising a network of ~~dykes~~dikes which are connected to one another by ~~crossing points~~intersections, which ~~dykes~~dikes delimit openings, the ~~thickness~~height of the ~~crossing points~~intersections not being equal to the ~~thickness~~height of the ~~dykes~~dikes only on the side of the screen material opposite to the flat side, wherein the height of the intersections is greater than the height of the dikes, wherein the difference between the height of the intersections and the height of the dikes is in the range from 20-250 micrometers, and wherein the screen material is electroformed.

2. (Canceled)

3. (Canceled)

4. (Currently Amended) Screen material according to claim 3~~1~~, wherein the difference is in the range from 100-200 ~~micrometres~~micrometers.

5. (Currently Amended) Screen material according to claim 1, wherein the ~~crossing points~~intersections have an apex angle of less than 120°.

6. (Original) Screen material according to claim 1, wherein the screen material is in the form of a seamless cylinder.

7. (Canceled)

8. (Currently amended) Method for manufacturing metal screen material having a flat side without projecting parts, comprising a network of ~~dykes~~dikes which are connected to one another by ~~crossing points~~intersections, which ~~dykes~~dikes delimit openings, comprising at least one or more growth steps for electrolytically thickening a flat screen skeleton in an electroplating bath under controlled conditions, in such a manner that in at least one growth step the growth rate of the ~~crossing points~~intersections is not equal to the growth rate of the ~~dykes~~dikes, so that

in the screen material the ~~thickness~~height of the ~~crossing points~~intersections is ~~not equal to~~
greater than the ~~thickness~~height of the ~~dykes~~dikes only on the side of the screen material
opposite to the flat side.

9. (Original) Method according to claim 8, wherein the controlled conditions comprise
a forced flow of the bath liquid through the screen skeleton.

10. (Original) Method according to claim 9, wherein the flow rate of the bath liquid is in
the range from 200 l/dm² to 600 l/dm².

11. (Original) Method according to claim 8, wherein the bath liquid comprises a
brightener in a concentration in the range from 200-500 g/l.

12. (Original) Method according to claim 11, wherein the bath liquid comprises a
brightener having properties of the first and second classes.

13. (Original) Method according to claim 8, wherein the current density is in the range
from 5 to 40 A/dm².

14. (Cancelled)

15. (Original) Assembly of a support screen and a perforating screen, in which the
support screen comprises screen material according to claim 1.

16. (Currently amended) Method for manufacturing an assembly of a tubular support
screen and a tubular perforating screen, in particular cylindrical seamless screens, at least
comprising a step of shrinking the perforating screen onto the support screen, wherein the
support screen comprises screen material having a flat side without projecting parts, comprising
a network of ~~dykes~~dikes which are connected to one another by ~~crossing points~~intersections,
which ~~dykes~~dikes delimit openings, the ~~thickness~~height of the ~~crossing points~~intersections ~~not~~
being equal togreater than the ~~thickness~~height of the ~~dykes~~dikes only on the side of the screen
material opposite to the flat side.

17. (Original) Method according to claim 16, wherein a cylindrical support screen is
subjected to a heat treatment at elevated temperature, so that a support screen with a defined

outer diameter (OD) is obtained, and in that a cylindrical perforating screen with an inner diameter (ID) which is slightly greater than the outer diameter (OD) of the support screen is fitted over the support screen, and the unit comprising support screen and perforating screen is subjected to a heat treatment at a temperature which is lower than the temperature used for the heat treatment of the support screen, for a sufficient time to shrink the perforating screen onto the support screen.

18. (Currently amended) Method for manufacturing an assembly of a tubular support screen and a tubular perforating screen, in particular cylindrical seamless screens, at least comprising a step of arranging a deformed support screen in the perforating screen and restoring the original shape of the support screen, wherein the support screen comprises screen material having a flat side without projecting parts, comprising a network of dykesdikes which are connected to one another by ~~crossing points~~intersections, which dykesdikes delimit openings, the thicknessheight of the ~~crossing points~~intersections ~~not being equal to greater than~~ the thicknessheight of the dykesdikes only on the side of the screen material opposite to the flat side.

19. (Original) Method according to claim 18, wherein to restore the original shape of the support screen, an inflatable container is placed into the support screen and is then pressurized.

20. (Original) Method according to claim 18, wherein the inner diameter of the perforating screen is slightly smaller than the outer diameter of the support screen.

21. (Currently amended) Method for manufacturing an assembly of a tubular support screen and a tubular perforating screen, in particular cylindrical seamless screens, at least comprising a step of pushing the perforating screen over the support screen with the aid of a pressurized fluid, wherein the support screen comprises screen material having a flat side without projecting parts, comprising a network of dykesdikes which are connected to one another by ~~crossing points~~intersections, which dykesdikes delimit openings, the thicknessheight of the ~~crossing points~~intersections ~~not being equal to greater than~~ the thicknessheight of the dykesdikes only on the side of the screen material opposite to the flat side.

22. (Canceled)

23. (Previously presented) Method for perforating film material, wherein the film material is perforated using an assembly of a support screen and a perforating screen, in which the support screen comprises screen material according to claim 1.

24. (Original) Assembly of a support screen and a perforating screen, in which the support screen comprises screen material obtained using the method according to claim 8.

25. (Currently amended) Method according to claim 18, at least comprising a step of arranging a deformed support screen in the perforating screen and restoring the original shape of the support screen, wherein a support screen obtained using the method according to claim 8 is used, which comprises at least one or more growth steps for electrolytically thickening a flat screen skeleton in an electroplating bath under controlled conditions, in such a manner that in at least one growth step the growth rate of the ~~crossing points~~intersections is not equal to the growth rate of the ~~dykes~~dikes, so that in the screen material the ~~thickness~~height of the ~~crossing points~~intersections is ~~not equal to~~greater than the ~~thickness~~height of the ~~dykes~~dikes only on the side of the screen material opposite to the flat side.

26. (Currently amended) Method according to claim 21, at least comprising a step of pushing the perforating screen over the support screen with the aid of a pressurized fluid, wherein a support screen obtained using the method according to claim 8 is used, which comprises at least one or more growth steps for electrolytically thickening a flat screen skeleton in an electroplating bath under controlled conditions, in such a manner that in at least one growth step the growth rate of the ~~crossing points~~intersections is not equal to the growth rate of the ~~dykes~~dikes, so that in the screen material the ~~thickness~~height of the ~~crossing points~~intersections is ~~not equal to~~greater than the ~~thickness~~height of the ~~dykes~~dikes only on the side of the screen material opposite to the flat side.

27.-29. (Canceled)